



IRON ORE

ELEMENT	IRON ORE LUMPS TYPICAL	IRON ORE FINES TYPICAL
Iron as Fe	63.50% Basis	63.50% Basis
Silica as SiO ₂	3.50% Max	3.50% Max
Alumina as Al ₂ O ₃	3.50% Max	3.50% Max
Sulphur as S	0.05% Max	0.05% Max
Phosphorus as P	0.07% Max	0.07% Max
Moisture dried at 105°C	6.00% Max	6.00% Max
PARTICLE SIZE ANALYSIS		
Above 40mm	5.00% Max	
Between 6 & 40 mm	80.00% Min	
Below 6 mm	15.00% Max	
Above 10 mm		15.00% Max
Below 10 mm		85.00% Min
Below 150 Micron		40.00% Max

PACKING

IN BULK