



POTASH FELDSPAR

ELEMENT	TYPICAL
Potash as K ₂ O	11.89%
Soda as Na ₂ O	3.54%
Titanium as TiO ₂	0.00%
Iron as Fe ₂ O ₃	0.10%
Alumina as Al ₂ O ₃	18.94%
Silica as SiO ₂	65.18%
Manganese as MnO	0.00%
Manganese as MgO	0.00%
Calcium as CaO	0.00%
LOI at 1000°C	0.30%
FIRING PROPERTIES	
COLOUR	WHITE
MELTING TEMPERATURE	1180 °C

PACKING

- LUMPS - IN BULK
- POWDER - AS PER BUYER'S REQUIREMENT